





LS102 (29102) EPOBUILD PRIMER 2K



1000 ml +
500 ml +
0-150 ml


Pot life at 20°C:
4 hours




22-30" DIN4
at 20 °C



Ø 1,6-1,9 mm
4 Atm
HVLP:
Ø 1,4-1,8 mm
2-2,5 Atm
N° coats: 2



70-120 µ



Air drying at 20° C
Tack-free, handling: 5 h
Through-dry: 48 h
Low bake at 60° C:
60 min.

DESCRIPTION

Two-pack epoxy primer with high filling power.

USE

Suitable as a primer for Truck Refinish and Industry in general.

CHARACTERISTICS

- Easy application
- Very good adhesion on:
 - Steel
 - Electro-galvanized and hot dip galvanized steel
 - Aluminium and its alloys
- Good anticorrosive power
- Good vertical stability
- Very good filling power
- Good sanding
- Possible application by wet-on-wet and dry-on-dry systems
- Chromate-free

SUBSTRATE PREPARATION

Black steel sheet: microsandblast, sand.

Steel: degrease carefully with 00695 SILICONE REMOVER SLOW, and sand or sandblast.

Aluminium and its alloys: degrease carefully with 00695 SILICONE REMOVER SLOW. Sandblast or sand or rub down carefully.

Electro-galvanized steel : degrease carefully with 00695 SILICONE REMOVER SLOW.

Hot dip galvanized steel: degrease with 00695 SILICONE REMOVER SLOW and sand or rub down.

Fibreglass: degrease with 00695 SILICONE REMOVER SLOW and sand if necessary.

APPLICATION

Spray.

Mixing ratio:

	weight	volume
LS102 EPOBUILD PRIMER (derived from binder 29102)	1000 g	1000 ml
29302 LECHSYS EPOBUILD PRIMER HARDENER	300 g	500 ml
00516 LECHSYS EPODUR THINNER or	0-100 g	0-150 ml
00556 LECHSYS EPODUR PF THINNER *		

***for extra-EEC countries only**

Pot life at 20 °C: 4 hours
Application viscosity at 20 °C: 22-30" DIN 4
Ø Air cap: traditional 1,6 - 1,9 mm; HVLP 1,4 - 1,8 mm
Air pressure: traditional 3,5 - 4,5 Atm; HVLP 2 - 2,5 Atm
N° of coats: 2
Suggested thickness: 70 - 120 µ
Theoretic coverage: 1 l of mixture = 4,5 m² at 100 µ
1 kg of mixture = 3,5 m² at 100 µ

DIR 2004/42/CE: Primer IIB/c – VOC ready for use 540 g/l
This product ready for use contains at most 500 g/l VOC

DRYING

Air drying at 20°C:

Dust-free: 15-20 min.
Handling: 5 hours
Sanding after 18-20 hours
Through-drying: 48 hours

Low bake at 60°C:

60 min.

SANDING AND SUGGESTED OVERCOATING

It can be puttied after 8-10 h at 20°C:

Dry-on-dry system

Sand dry with grit paper P280-320

Wet-on-wet system

Overcoating from 1 h to 12 h (at 20°C) with acrylic (ACRITOP) or polyurethane enamels (ISOLACK).

NOTES

It is not recommended to apply the mixture at temperatures below 15°C.

This product is chromate- and lead-free. It is recommended to avoid adding the base colours 29011, 29012 and 29026 in the formulations, as they contain lead and would make the final product lose its non-toxic characteristics.

Search the formulation to produce under "SOTT" on the Data Box and choose the colour in the respective colour fan.

TECHNICAL DATA SHEET N° 0482-GB
UPDATED 02/2014

All information contained in this data sheet is the result of carefully controlled tests and is correct to the best of Lechler's knowledge at the time of issue. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated and the manner of use is the sole responsibility of the user. FOR PROFESSIONAL USE ONLY.