

AIRCOLOR Isofill

HIGH THICKNESS PRIMER - Aerosol -



DATA SHEET **J45**

Version: 250306



DESCRIPTION

ISOFill is a primer ready-to-use in aerosol format 1K. Its unique formula offers exceptional coverage and superior thickness, making it the ideal choice for auto body repair work.

Its economical and easy-to-use application makes it a practical solution for touch-ups and minor repairs. In addition, its fast drying time facilitates an efficient and streamlined process, allowing users to complete their projects in a short time.

ISOFill provides a high quality finish and offers a solid base for the final topcoat. With its excellent adhesion and sandability, it guarantees professional and durable results with every application.

PHYSICAL CHARACTERISTICS

Nature: Nitrosynthetic

Colour: Isofill - White

Isofill - Grey Light

Isofill - Grey Dark

Aircolor

Specific weight: 0.9 kg/l at 20°C

Propellant: Dimethyl ether

Aerosol Pressure: 4 bar at 20°C

Dry film thickness: 25-35 microns 2-3 coats

Yield: 4 m²/aerosol

VOC: 685 g/l

Dry residue: 39 %

METHOD OF APPLICATION

PROCESS		Putty	OEM paint	Aluminium	Galvanized	Steel	Cataphoresis
	P360	✓	✓	✓	✓	✓	✓
	DA93	✓	✓	✓	✓	✓	✓

AIRCOLOR Isofill



HIGH THICKNESS PRIMER - Aerosol -



DATA SHEET **J45**

Version: 250306

METHOD OF APPLICATION

						 P600	
2-3	10-20	2-3	5' or matt	10°C	15'	1h30'-2h	2h
				20°C	10'	1h	1h
				30°C	7'	45'	45'-1h

REMARKS

Shake the aerosol before use for 2-3 minutes after hearing the noise of the mixer. Protect areas that are not to be painted.

CLEANING OF THE EQUIPMENT

Once the product has been applied, clean the nozzle by spraying upside down until only gas comes out.

SECURITY

Once the has been product label consulted. For further information refer to the safety data sheet. Observe health and safety at work and waste disposal directives.

After using the product, clean the nozzle by spraying upside down until only gas comes out.

STORAGE

Keep in a cool and ventilated place, avoiding direct exposure to sunlight. Store between +5°C and +30°C.

SHELF LIFE

One year in original unopened packaging.

SUGGESTIONS

Use Isofill as a guide to check that the edges where putty has been applied are well profiled.

For any technical information, please contact our Customer Service or Technical Department.

These products are for professional use only. The Safety Data Sheet must be consulted before use and the precautionary warnings on the product packaging must be observed. Their correct use, in accordance with their purpose and respecting the technical and safety data provided in these documents, is the sole and exclusive responsibility of the user. ROBERLO S.A.U. declines any responsibility due to the incorrect use of any product.

The information included in this documentation is based on our scientific and technical knowledge at the date of issue. ROBERLO S.A.U. reserves the right to modify and/or discontinue all or part of the information at any time and without prior notice. It is the user's responsibility to verify that the information is up to date. The latest version of this document replaces all previous versions.

All clauses included in this document are applicable to any future changes or modifications